

ASTM A106 Seamless Carbon Steel Pipe - Data Sheet

Mejor Steel, export sourcing for steel pipe and OCTG | Request a quotation: <https://mejorsteel.com/get-a-quote/>

Specifications

Outer diameter	1/8" - 48" (10.3 - 1219 mm)
Wall thickness	SCH 10 - SCH XXS
Schedule	SCH 10, 20, 40, 60, 80, 100, 120, 140, 160, XXS
Length	SRL 5.8 m, DRL 11.8 m, 20 FT, 40 FT, or custom
Ends	Plain, beveled, threaded
Surface treatment	Black painting, varnish, galvanized, 3PE, FBE
Manufacturing process	Hot rolled seamless, cold drawn seamless
Pressure rating	High temperature and high pressure service

Grades supplied and minimum properties

Grade	Yield strength	Tensile strength
Grade A	205 MPa (30,000 psi)	330 MPa (48,000 psi)
Grade B	240 MPa (35,000 psi)	415 MPa (60,000 psi)
Grade C	275 MPa (40,000 psi)	485 MPa (70,000 psi)

- Grade A
- Grade B
- Grade C

Inspection & testing

Packaging	Sea-worthy export packing: bundled by size, plastic caps on both ends, corrosion protection on request, stencilled with size, grade and heat number.
MOQ	One bundle or one truckload; mixed sizes within a bundle accepted.
Lead time	Stock sizes: 7-15 days. Mill run / non-stock: 4-6 weeks after order confirmation.

- Ultrasonic testing
- Hydrostatic pressure test
- Tensile and yield testing
- Flattening, bend and hardness test
- Chemical composition analysis

Page: <https://mejorsteel.com/steel-pipe/astm-a106-seamless-steel-pipe/> | Everything in this data sheet is taken from the published page. The governing standard, MOQ, lead time and price are confirmed on request.